

In the Claims:

Please cancel Claims 6-12, Claim 18(b) and Claim 19(b). Amend Claims 18 and 19. The changes in these claims are shown with ~~strikethroughs~~ for deleted matter and underlines for added matter. A complete listing of the claims with proper claim identifiers is set forth below.

1.-14. (Cancelled)

15. (Previously Presented) An acrylic elastomer composition comprising an acrylic elastomer (A), and a polyorganosiloxane-containing graft polymer (B) wherein the graft component of the polyorganosiloxane-containing graft polymer (B) contains 5 to 99.5 percent by weight of an alkyl methacrylate, and 95 to 0.5 percent by weight of an alkyl acrylate on the basis of the entirety of the graft component, and wherein the graft component of the polyorganosiloxane-containing graft polymer (B) contains 0.5 to 50 percent by weight of n-butyl methacrylate as an essential alkyl methacrylate component on the basis of the entirety of the grant component.

16. (Previously Presented) An acrylic elastomer composition comprising an acrylic elastomer (A), and a polyorganosiloxane-containing graft polymer (B), wherein the polyorganosiloxane-containing graft polymer (B) comprises 5 to 40 percent by weight of a graft component, and 95 to 60 percent by weight of a poly organosiloxane, and wherein the graft component of the polyorganosiloxane-containing graft polymer (B) contains 0.5 to 10 percent by weight of methacrylic acid or acrylic acid on the basis of the entirety of the graft component.

17. (Previously Presented) An acrylic elastomer composition comprising an acrylic elastomer (A), and a polyorganosiloxane-containing graft polymer (B), wherein the acrylic elastomer (A) comprises a mixture of acrylic block copolymers including an acrylic block copolymer (E-1) comprising an acrylic polymer block (a1) and a methacrylic polymer block (b), and an acrylic block copolymer (E-2) comprising an acrylic polymer block (a2) different from the acrylic polymer block (a1) and the methacrylic polymer block (b), the acrylic block copolymer (E-1) having a low-

temperature brittle temperature which is at least 5°C higher than that of the acrylic block copolymer (E-2).

18. (Currently Amended) The acrylic elastomer composition according to any one of claims 6-15, 16 or 17, further comprising 0.1 to 10 parts by weight of a lubricant, 0.1 to 100 parts by weight of an inorganic filler, and 0.1 to 100 parts by weight of a thermoplastic resin on the basis of 100 parts by weight of the acrylic elastomer (A).

19. (Currently Amended) A molded product comprising the acrylic elastomer composition according to any one of claims 6-15, 16 or 17.

20. (Original) An automobile, electric or electronic part comprising the molded product of the acrylic elastomer composition according to claim 19.